



Europäisches Patentamt
European Patent Office
Office européen des brevets



(11) Publication number:

0 672 954 A2

(12)

EUROPEAN PATENT APPLICATION

(21) Application number: 95200567.6

(51) Int. Cl.⁶: G03F 7/038, G03F 7/039

(22) Date of filing: 08.03.95

(30) Priority: 14.03.94 US 212434

(43) Date of publication of application:
20.09.95 Bulletin 95/38

(84) Designated Contracting States:
BE DE FR GB NL

(71) Applicant: **EASTMAN KODAK COMPANY**
343 State Street
Rochester,
New York 14650-2201 (US)

(72) Inventor: **Haley, Neil Frederick, c/o Eastman Kodak Company**
Patent Department,
343 State Street
Rochester,
New York 14650-2201 (US)
Inventor: **Corbiere, Steven Leo, c/o Eastman Kodak Company**
Patent Department,
343 State Street
Rochester,
New York 14650-2201 (US)

(74) Representative: **Nunney, Ronald Frederick Adolphe et al**
Kodak Limited
Patent Department
Headstone Drive
Harrow
Middlesex HA1 4TY (GB)

(54) **Radiation-sensitive composition containing a resole resin, a novolac resin, an infrared absorber and a triazine and use thereof in lithographic printing plates.**

(57) A radiation-sensitive composition especially adapted to prepare a lithographic printing plate that is sensitive to both ultraviolet and infrared radiation and capable of functioning in either a positive-working or negative-working manner is comprised of (1) a resole resin, (2) a novolac resin, (3) a haloalkyl-substituted s-triazine and (4) an infrared absorber. The solubility of the composition in aqueous alkaline developing solution is both reduced in exposed areas and increased in unexposed areas by the steps of imagewise exposure to activating radiation and heating.

EP 0 672 954 A2

FIELD OF THE INVENTION

This invention relates in general to novel radiation-sensitive compositions and in particular to the use of such compositions in lithographic printing plates. More specifically, this invention relates to radiation-sensitive compositions comprising both a resole resin and a novolac resin and to lithographic printing plates comprising an imaging layer formed from such radiation-sensitive compositions.

BACKGROUND OF THE INVENTION

The art of lithographic printing is based upon the immiscibility of oil and water, wherein the oily material or ink is preferentially retained by the image area and the water or fountain solution is preferentially retained by the non-image area. When a suitably prepared surface is moistened with water and an ink is then applied, the background or non-image area retains the water and repels the ink while the image area accepts the ink and repels the water. The ink on the image area is then transferred to the surface of a material upon which the image is to be reproduced; such as paper, cloth and the like. Commonly the ink is transferred to an intermediate material called the blanket which in turn transfers the ink to the surface of the material upon which the image is to be reproduced.

A very widely used type of lithographic printing plate has a light-sensitive coating applied to an aluminum base support. The coating may respond to light by having the portion which is exposed become soluble so that it is removed in the developing process. Such a plate is referred to as positive-working. Conversely, when that portion of the coating which is exposed becomes hardened, the plate is referred to as negative-working. In both instances the image area remaining is ink-receptive or oleophilic and the non-image area or background is water-receptive or hydrophilic. The differentiation between image and non-image areas is made in the exposure process where a film is applied to the plate with a vacuum to insure good contact. The plate is then exposed to a light source, a portion of which is composed of UV radiation. In the instance where a positive plate is used, the area on the film that corresponds to the image on the plate is opaque so that no light will strike the plate, whereas the area on the film that corresponds to the non-image area is clear and permits the transmission of light to the coating which then becomes more soluble and is removed. In the case of a negative plate the converse is true. The area on the film corresponding to the image area is clear while the non-image area is opaque. The coating under the clear area of film is hardened by the action of light while the area not struck by light is removed. The light-hardened surface of a negative plate is therefore oleophilic and will accept ink while the non-image area which has had the coating removed through the action of a developer is desensitized and is therefore hydrophilic.

The manufacture of a printing plate which can be employed as either a positive-working plate or a negative-working plate has been proposed heretofore. Such a plate has the advantage of increased versatility since either positive or negative originals can be used.

One example of a printing plate which can be employed as either a positive-working plate or a negative-working plate is that described in British Patent No. 2,082,339, published March 3, 1982 and in U.S. Patent 4,927,741, issued May 22, 1990. These patents describe a lithographic printing plate in which the imaging layer comprises a resole resin and an orthoquinone diazide and, optionally, also contains a novolac resin. Such a plate can be used as a positive-working plate by a process comprising the steps of imagewise exposure and development with an aqueous alkaline developing solution to remove the coating from the exposed areas. Alternatively, it can be used as a negative-working plate by a process comprising the steps of imagewise exposure, heating of the plate to convert the coating in the exposed areas to an insoluble form, overall exposure of the plate to radiation to render previously unexposed areas soluble, and development with an aqueous alkaline developing solution to remove such soluble areas.

A further example of a printing plate which can be employed as either a positive-working plate or a negative-working plate is that described in U.S. Patent 4,708,925, issued November 24, 1987. This patent describes a lithographic printing plate in which the imaging layer comprises a phenolic resin and a radiation-sensitive onium salt. As described in the patent, the interaction of the phenolic resin and the onium salt produces an alkali-insoluble composition which is restored to alkali-solubility upon photolytic decomposition of the onium salt. The printing plate can be utilized as a positive-working plate or as a negative-working plate using the same process steps as are described hereinabove in regard to the plates of British Patent 2,082,339 and U.S. Patent 4,927,741.

The radiation-sensitive composition described in U.S. Patent 4,708,925 is useful for the preparation of a direct laser addressable plate. Digital imaging information can be used to image the plate without the need to utilize an imaging master such as a photographic transparency.

The hereinabove described printing plates of the prior art which can be employed as either a positive-working plate or a negative-working plate are lacking in one or more desirable features. Thus, the plates described in British Patent No. 2,082,339 are not infrared-sensitive and thus cannot be digitally imaged by a laser which emits in the infrared region. Moreover, both the plates of British Patent No. 2,082,339 and U.S. Patent 4,708,925 require two exposure steps in order to be utilized as a negative-working plate, i.e., an imagewise exposure and a subsequent overall exposure. This adds greatly to the cost and complexity of the process. The difficulties of carrying out a process requiring multiple exposure steps, while meeting the requirements of the trade for high speed processing, are described in U.S. Patent 4,927,741.

Radiation-sensitive compositions comprised of (1) a resole resin, (2) a novolac resin, (3) a latent Bronsted acid and (4) an infrared absorber are described in U.S. Patent 5,372,907, issued December 13, 1994. Such compositions are useful in preparing a lithographic printing plate which can be employed as either a positive-working plate or a negative-working plate. To utilize this lithographic printing plate as a positive-working plate requires that it be imagewise exposed to activating radiation, thereby rendering the exposed areas alkali-soluble, and contacted with an aqueous alkaline developing solution to remove the exposed areas. To utilize it as a negative-working plate requires the steps of imagewise exposure to activating radiation, heating of the plate to provide reduced solubility in exposed areas and increased solubility in unexposed areas, and contact with an aqueous alkaline processing solution to remove the unexposed areas. In contrast with the printing plates of British Patent No. 2,082,339 and U.S. Patent 4,708,925, use of both a resole resin and a novolac resin is essential and the use of two exposure steps is not necessary.

While the radiation-sensitive compositions of U.S. Patent 5,372,907 represent a major advance in the art, they would benefit from a further improvement in their properties, especially in regard to enhanced sensitivity in the ultraviolet region of the spectrum. It is toward the objective of providing such further improvement that the present invention is directed.

SUMMARY OF THE INVENTION

In accordance with this invention, a novel radiation-sensitive composition is comprised of (1) a resole resin, (2) a novolac resin, (3) a latent Bronsted acid and (4) an infrared absorber and is characterized in that the latent Bronsted acid is a haloalkyl-substituted s-triazine. This composition has many different uses, for example, it is useful as a photoresist, but it is especially useful in the preparation of a lithographic printing plate comprised of a support and an imaging layer formed from the radiation-sensitive composition. The resulting printing plate has many advantageous characteristics. In particular, the plate is:

- (1) infrared sensitive to facilitate digital imaging by exposure to infrared radiation;
- (2) ultraviolet sensitive to facilitate optical imaging by exposure to ultraviolet radiation through an imaging master; and
- (3) substantially insensitive to visible radiation so as to facilitate room-light-handling.

The characteristics of the novel printing plate described herein are such that imagewise exposure to activating radiation followed by heating results in opposite effects in exposed and unexposed areas. In particular, in exposed areas the imaging layer becomes less soluble in an aqueous alkaline developing solution while in unexposed areas it becomes more soluble in such solution. These opposing effects contribute to both high speed and high contrast, both of which are highly desirable attributes in a lithographic printing plate.

Since the printing plate of this invention is infrared sensitive, digital imaging information can be conveniently utilized to form continuous or halftone images using a suitable source of infrared radiation such as a laser diode emitting in the infrared region. Since the printing plate of this invention is also ultraviolet sensitive, it can also be conveniently imaged so as to form continuous or halftone images by ultraviolet exposure through a suitable imaging master such as a silver halide film. Because of these characteristics, the same plate can be utilized in equipment intended for input of electronic data by writing with a laser or in the type of equipment that is commonly employed to carry out ultraviolet exposure of lithographic printing plates. It is thus an easy matter to combine digital or electronic imaging techniques with conventional optical imaging techniques, i.e., to use both types of imaging with the same printing plate. Accordingly, information not available in an electronic format can be added by optical imaging techniques to complete the imaging of the lithographic printing plate when it is desired to do so.

To utilize the lithographic printing plate of this invention as a positive-working plate requires that it be imagewise exposed to activating radiation, thereby rendering the exposed areas alkali-soluble, and contacted with an aqueous alkaline developing solution to remove the exposed areas. To utilize it as a negative-working plate requires the steps of imagewise exposure to activating radiation, heating of the plate

to provide reduced solubility in exposed areas and increased solubility in unexposed areas, and contact with an aqueous alkaline processing solution to remove the unexposed areas. In contrast with the printing plates of British Patent No. 2,082,339 and U.S. Patent 4,708,925, use of both a resole resin and a novolac resin is essential and the use of two exposure steps is not necessary.

While applicants do not wish to be bound by any theoretical explanation for the manner in which their invention functions, it is believed that it is based upon an acid-catalyzed chemical amplification mechanism which occurs upon heating of the exposed plate. This mechanism reduces the solubility of the exposed areas by hardening the mixture of resins. At the same time, it increases the solubility of the unexposed areas. The mechanism whereby it accomplishes the latter effect is not clearly understood.

The functioning of the plate as a negative-working plate is critically dependent upon the use of a mixture of a resole resin and a novolac resin since the use of either resin alone does not provide a useful developed image.

Exposure of the plate to infrared radiation is believed to decompose both the infrared absorber and the haloalkyl-substituted s-triazine in the exposed areas. The decomposition products are believed to catalyze a reaction between the resole resin and the novolac resin to form a matrix which after heating is insoluble in aqueous alkaline developing solution.

Exposure to ultraviolet radiation also results in decomposition of the haloalkyl-substituted s-triazine to generate a halogen acid which catalyzes the matrix-forming reaction between the resole resin and the novolac resin. The plate has a high degree of sensitivity in both the ultraviolet and infrared regions of the spectrum. In other words, it can be exposed at two different wavelengths.

DESCRIPTION OF THE PREFERRED EMBODIMENTS

As indicated hereinabove, the radiation-sensitive composition of this invention is comprised of (1) a resole resin, (2) a novolac resin, (3) a haloalkyl-substituted s-triazine and (4) an infrared absorber.


Resole resins are well known and widely available on a commercial basis. They are phenolic resins which are obtained by reaction of phenolic compounds with aldehydes. A typical example of a resole resin useful in this invention is a resin prepared from bis-phenol A and formaldehyde. A preferred resole resin that is available on a commercial basis is UCAR phenolic resin BKS-5928 which is available from Union Carbide Corporation. Novolac resins are also well known and widely used on a commercial basis. They are phenolic resins which are also obtained by reaction of phenolic compounds with aldehydes but under different reaction conditions than those that produce resole resins. A typical example of a novolac resin useful in this invention is a resin prepared from m-cresol and formaldehyde. A preferred novolac resin that is available on a commercial basis is N-9P NOVOLAK available from Eastman Kodak Company.

Differences between resole resins and novolac resins and the processes used in their preparation are described in U.S. Patent 4,708,925 and in British Patent No. 2,082,339. The resole resins and the novolac resins specifically described in these patents are also useful in the present invention, but the invention requires the use of both a resole resin and a novolac resin, whereas use of both resins is not required in either of these patents.

The radiation-sensitive composition of this invention must contain both a resole resin and a novolac resin. If the resole resin is omitted, the steps of imagewise exposure and heating are not able to provide a useful means of negative imaging since contact with an aqueous alkaline developing solution will not remove the coating from the unexposed areas and the printing plate processed in this manner is not useful. If the novolac resin is omitted, the steps of imagewise exposure and heating are again not able to provide a useful means of imaging since contact with an aqueous alkaline developing solution will remove the coating from both exposed and unexposed areas and the printing plate processed in this manner is not useful.

The third essential ingredient of the radiation-sensitive composition of this invention is a haloalkyl-substituted s-triazine. The haloalkyl-substituted s-triazines are well known photolytic acid generators. Use of these compounds for this purpose is described, for example, in U.S. Patent 3,779,778.

Preferred haloalkyl-substituted s-triazines for use in this invention are compounds of the formula:




wherein R_1 is a substituted or unsubstituted aliphatic or aromatic radical and R_2 and R_3 are, independently, haloalkyl groups.

In the above formula, it is especially preferred that R_2 and R_3 are haloalkyl groups of 1 to 4 carbon atoms.

5 R_1 can include any substituent which does not adversely affect the photolytic acid-generating capability of the s-triazine compound. Such substituents include alkyl groups and alkoxy groups.

Particularly preferred haloalkyl-substituted s-triazines for use in this invention are compounds of the formula:

10




15

wherein R_1 is a substituted or unsubstituted aliphatic or aromatic radical and each X is, independently, a halogen atom.

20 The most preferred haloalkyl-substituted s-triazines for use in this invention are compounds of the formula:

25



30


wherein R is an aryl group of 6 to 15 carbon atoms, such as, for example, phenyl or naphthyl.

Specific examples of haloalkyl-substituted s-triazines that are preferred for use in this invention include the following compounds:

35

T-1





40



45

50

55

T-2T-3T-4T-5

The fourth essential ingredient of the radiation-sensitive composition of this invention is an infrared absorber. The infrared absorber renders the composition sensitive to infrared radiation and makes the printing plate useful as a direct laser addressable plate which can be imaged by exposure to a laser which emits in the infrared region.

The infrared absorber can be a dye or pigment. A very wide range of such compounds is well known in the art and includes dyes or pigments of the squarylium, croconate, cyanine, merocyanine, indolizine,

pyrylium and metal dithiolene classes. It is preferred that the infrared absorber fragment upon exposure to the activating radiation since the decomposition products promote increased contrast between image and non-image areas and thereby help in the development process.

Additional infrared absorbers that are of utility in this invention include those described in U.S. Patent 5,166,024, issued November 24, 1992. As described in the '024 patent, particularly useful infrared absorbers are phthalocyanine pigments.

As explained hereinabove, the four essential ingredients of the radiation-sensitive composition of this invention are a resole resin, a novolac resin, a haloalkyl-substituted s-triazine and an infrared absorber. Other ingredients which can optionally be incorporated in the composition include colorants, stabilizers, additional sensitizers, exposure indicators and surfactants.

The thickness of the imaging layer in the printing plates of this invention can vary widely. Typically, a dry thickness in the range of from 0.5 to 2 micrometers, more preferably from 1 to 1.5 micrometers is suitable.

The lithographic printing plates of this invention can employ any of the supports conventionally used for lithographic printing plates, including supports formed from aluminum or other metals, supports formed from polymers such as polyesters, and supports formed from polymer-coated paper. A preferred support material is grained and anodized aluminum.

To form the printing plate, the resole resin, novolac resin, haloalkyl-substituted s-triazine and infrared absorber are dissolved or dispersed in a suitable solvent in appropriate proportions and coated on the support using such well-known coating techniques as spin coating or hopper coating. Preferred solvents include acetone and 1-methoxy-2-propanol. The resole resin and novolac resin may be each incorporated in the coating composition in an amount of from 1.5 to 6 percent by weight, more preferably from 2.5 to 5.5 percent by weight, and most preferably from 4.5 to 5.3 percent by weight. The haloalkyl-substituted s-triazine may be incorporated in the coating composition in an amount of from 0.1 to 2 percent by weight, more preferably from 0.3 to 1.5 percent by weight, and most preferably from 0.5 to 1 percent by weight. The infrared absorber may be incorporated in the coating composition in an amount of from 0.15 to 1.1 percent by weight, more preferably from 0.45 to 0.9 percent by weight, and most preferably from 0.68 to 0.88 percent by weight.

Suitable conditions for drying the layer include heating for a period of from 0.5 to 10 minutes at a temperature in the range of from 20 °C to 150 °C.

The lithographic printing plates of this invention can be exposed with a laser diode which emits radiation in the near-infrared region of the spectrum. Such laser diodes provide the advantage of both low cost and low energy consumption. The lithographic printing plates can also be exposed with conventional ultraviolet radiation sources, including carbon arc lamps, mercury vapor lamps, fluorescent lamps, tungsten filament lamps and photoflood lamps.

Exposure of the printing plate results in the formation of an image which is typically visible as a reddish-yellow color on a light green background.

A particularly suitable exposing device is a laser diode with a maximum output at about 800 nanometers. Such a device is typically capable of decomposing both the haloalkyl-substituted s-triazine and the infrared absorber in the exposed areas. The products from the thermal decomposition are mainly strong acids which are effective in crosslinking the resins, thereby altering solubility in aqueous alkaline developing solution.

As described hereinabove, in a negative-working process the imagewise-exposed plate is heated in a step that is referred to as a post-exposure bake or PEB. The heating step may be conducted at a temperature in the range of from 75 °C to 150 °C for a period of from 15 to 300 seconds. More preferably, the heating is for a period of from 30 to 90 seconds at a temperature in the range of from 90 °C to 110 °C. After the PEB is completed, the plate is then either hand processed or machine processed in an aqueous alkaline developing solution until the non-image areas are removed. This typically requires 30 to 120 seconds. A preferred aqueous alkaline developing solution is a silicate solution such as a six percent by weight aqueous solution of sodium meta-silicate. A suitable commercially available silicate solution for this purpose is KODAK AQUA-IMAGE POSITIVE DEVELOPER MX-1406-1 which is sold by Eastman Kodak Company. After contact with the aqueous alkaline developing solution, the plate is usually treated with a finisher such as gum arabic.

The number of printing impressions obtainable is primarily dependent upon use of a post development baking step. If no such baking step is used, the plate typically provides 60000 to 70000 impressions, whereas post development baking for about 5 minutes at about 250 °C typically provides 300000 to 350000 impressions. The number of impressions that can be attained before wear is detected can also be increased by increasing the coating weight.


It was surprising to find that use of a mixture of a resole resin and a novolac resin provides a printing plate which, upon post-exposure heating, undergoes reactions which both inhibit solubility of the exposed areas and enhance solubility of the unexposed areas. This feature, together with the feature of both ultraviolet and infrared sensitivity, provides a remarkably versatile printing plate. Thus, for example, with this printing plate, the major imaging technique used can be digital imaging with infrared radiation but conventional ultraviolet exposure can be used to add non-digital information to the printing process when such information is not available in a digital format. Higher speeds, greater contrast and simpler processing conditions are attainable because the image and non-image areas are affected in opposite directions at the same time. Prior to this invention, no known lithographic printing plate possessed all of these desirable features.

The invention is further illustrated by the following examples of its practice.

Example 1

To 100 milliliters of 1-methoxy-2-propanol there was added:

- (1) 10 milliliters of a 30% by weight solution of a resole resin (UCAR phenolic resin BKS-5928 available from Union Carbide Corporation) in a mixture of 2-butanone and 1-methoxy-2-propanol;
- (2) 10 milliliters of a 30% by weight solution of a novolac resin (N-9P NOVOLAK resin available from Eastman Kodak Company) in acetone;
- (3) 2.0 grams of triazine T-2 in 2 milliliters of acetonitrile; and
- (4) 0.5 grams of an infrared absorbing dye having the following structural formula:



dissolved in 10 milliliters of 1-methoxy-2-propanol.

The resulting solution was spin coated onto an electrochemically grained and anodized aluminum plate at 30 revolutions per minute for one minute and dried in a forced air oven at 100 °C for one minute. After cooling, the plate was imaged using a 500 milliwatt diode laser emitting a modulated pulse centered at 830 nanometers. After imaging, the plate was heated in a forced air oven at 100 °C for one minute, cooled and processed in a mechanical processor using KODAK AQUA IMAGE positive machine developer MX-1406-1. The resulting image was finished by applying a 5% solution of gum arabic and hand buffing with a cloth. The image had an estimated run length of 70000 impressions based on an accelerated wear test. A second plate, identical to the first, was baked at 250 °C for five minutes and had an estimated run length of 350000 impressions.

In comparison with the printing plate described in Example 1 of U.S. Patent 5,372,907, the printing plate described above exhibited greater developer latitude, faster roll-up and higher image density but lower print-out density.

Example 2

A lithographic printing plate, the same as that described in Example 1, was prepared except that 1.0 grams of triazine T-3 was used in place of the 2.0 grams of triazine T-2. Results similar to those described in Example 1 were achieved, except that the print-out density was higher.

Example 3

A lithographic printing plate, the same as that described in Example 1, was prepared except that 0.3 grams of triazine T-5 was used in place of the 2.0 grams of triazine T-2. Results similar to those described in Example 1 were achieved.

Example 4

A lithographic printing plate, the same as that described in Example 1, was prepared except that 0.5 grams of triazine T-1 was used in place of the 2.0 grams of triazine T-2. Results similar to those described in Example 1 were obtained, except that the print-out density was lower and the image density after processing was lower.

Comparative Example A


A lithographic printing plate, the same as that described in Example 1, was prepared except that the resole resin was omitted and an additional 10 milliliters of 1-methoxy-2-propanol was added. After exposing and processing in the same manner described in Example 1, the non-image areas remained, resulting in a useless printing plate.

Comparative Example B

A lithographic printing plate, the same as that described in Example 1, was prepared except that the novolac resin was omitted and an additional 10 milliliters of 1-methoxy-2-propanol was added. After exposing and processing in the same manner described in Example 1, the entire coating in both image and non-image areas was removed from the plate, resulting in a useless printing plate.


Claims

1. A radiation-sensitive composition comprising (1) a resole resin, (2) a novolac resin, (3) a haloalkyl-substituted s-triazine, and (4) an infrared absorber.
2. A radiation-sensitive composition as claimed in claim 1, wherein said resole resin is derived from bis-phenol A and formaldehyde.
3. A radiation-sensitive composition as claimed in claim 1, wherein said novolac resin is derived from m-cresol and formaldehyde.
4. A radiation-sensitive composition as claimed in any of claims 1 to 3, wherein said haloalkyl-substituted s-triazine has the formula:




wherein R_1 is a substituted or unsubstituted aliphatic or aromatic radical and R_2 and R_3 are, independently, haloalkyl groups.

5. A radiation-sensitive composition as claimed in any of claims 1 to 3, wherein said haloalkyl-substituted s-triazine has the formula:



wherein R_1 is a substituted or unsubstituted aliphatic or aromatic radical and each X is, independently, a halogen atom.


6. A radiation-sensitive composition as claimed in any of claims 1 to 3, wherein said haloalkyl-substituted s-triazine has the formula:




wherein R is an aryl group of 6 to 15 carbon atoms.

7. A radiation-sensitive composition as claimed in claim 1, wherein said haloalkyl-substituted s-triazine is represented by one of formulae I to V as follows:


I




II




III



IV



V



- 25 8. A radiation-sensitive composition as claimed in any of claims 1 to 7, wherein said infrared absorber is a squarylium, croconate, cyanine, merocyanine, indolizine, pyrylium or metal dithiolen dye or pigment.
9. A lithographic printing plate comprising a support and an imaging layer that is sensitive to both ultraviolet and infrared radiation and capable of functioning in either a positive-working or negative-working manner, the solubility of said imaging layer in aqueous alkaline developing solution being reduced in exposed areas and increased in unexposed areas by the steps of imagewise exposure to activating radiation and heating; said imaging layer comprising (1) a resole resin (2) a novolac resin, (3) a haloalkyl-substituted s-triazine and (4) an infrared absorber.
- 30 10. A lithographic printing plate as claimed in claim 9, wherein said imaging layer has a dry thickness in the range of from 0.5 to 2 micrometers.

(19)



Europäisches Patentamt

European Patent Office

Office européen des brevets



(11)

EP 0 672 954 A3

(12)

EUROPEAN PATENT APPLICATION

(88) Date of publication A3:
25.06.1997 Bulletin 1997/26

(51) Int. Cl.⁶: **G03F 7/038, G03F 7/039**

(43) Date of publication A2:
20.09.1995 Bulletin 1995/38

(21) Application number: **95200567.6**

(22) Date of filing: **08.03.1995**

(84) Designated Contracting States:
BE DE FR GB NL

(30) Priority: **14.03.1994 US 212434**

(71) Applicant: **EASTMAN KODAK COMPANY**
Rochester, New York 14650-2201 (US)

(72) Inventors:
• **Haley, Neil Frederick,**
c/o Eastman Kodak Company
Rochester, New York 14650-2201 (US)

• **Corbiere, Steven Leo,**
c/o Eastman Kodak Company
Rochester, New York 14650-2201 (US)

(74) Representative: **Nunney, Ronald Frederick**
Adolphe et al
Kodak Limited
Patent Department
Headstone Drive
Harrow Middlesex HA1 4TY (GB)

(54) **Radiation-sensitive composition containing a resole resin, a novolac resin, an infrared absorber and a triazine and use thereof in lithographic printing plates**

(57) A radiation-sensitive composition especially adapted to prepare a lithographic printing plate that is sensitive to both ultraviolet and infrared radiation and capable of functioning in either a positive-working or negative-working manner is comprised of (1) a resole resin, (2) a novolac resin, (3) a haloalkyl-substituted s-triazine and (4) an infrared absorber. The solubility of the composition in aqueous alkaline developing solution is both reduced in exposed areas and increased in unexposed areas by the steps of imagewise exposure to activating radiation and heating.

EP 0 672 954 A3

European Patent
Office

EUROPEAN SEARCH REPORT

Application Number

DOCUMENTS CONSIDERED TO BE RELEVANT			EP 95200567.6
Category	Citation of document with indication, where appropriate, of relevant passages	Relevant to claim	CLASSIFICATION OF THE APPLICATION (Int. Cl. 6)
D, P, X	<u>US - A - 5 372 907</u> (HALEY) * Totality * --	1-10	G 03 F 7/038 G 03 F 7/039
D, A	<u>US - A - 4 708 925</u> (NEWMAN) * Claims; column 1, lines 7-13; column 3, lines 40-46; column 7, lines 28-59 * --	1-4, 8, 9	
A	<u>US - A - 5 085 972</u> (VOGEL) * Claims; column 5, lines 35-43 * --	1, 4, 5, 9	
D, A	<u>GB - A - 2 082 339</u> (HORSELL GRAPHIC INDUSTRIES LIMITED) * Claims * ----	1-3, 9	
			TECHNICAL FIELDS SEARCHED (Int. Cl. 6)
			G 03 F
The present search report has been drawn up for all claims			
Place of search VIENNA		Date of completion of the search 08-04-1997	Examiner SCHÄFER
<p>CATEGORY OF CITED DOCUMENTS</p> <p>X : particularly relevant if taken alone Y : particularly relevant if combined with another document of the same category A : technological background O : non-written disclosure P : intermediate document</p> <p>T : theory or principle underlying the invention E : earlier patent document, but published on, or after the filing date D : document cited in the application L : document cited for other reasons & : member of the same patent family, corresponding document</p>			

EPO FORM 1503 01.82 (1/9401)